

CLAIMS

What is claimed is:

1. A laminate comprising:
 - a nonwoven web treated with a surfactant;
 - 5 a film comprising a core layer and at least one skin layer, the core layer comprising a percentage by weight of a micropore developing filler;
wherein the film is stretched in at least one direction to a percentage of its original size to become microporous, and thermally bonded to the surfactant treated nonwoven;
wherein the laminate is a breathable barrier compliant with ASTM F1670-95.
- 10 2. The laminate of claim 1 wherein the core layer comprises about 30% to about 75% by weight polyolefin resin and from about 70% to about 25% by weight of filler having an average size less than about 10 microns, the skin layer comprising a CATALLOY polymer.
3. The laminate of claim 1 wherein the core layer comprises about 35% to about 75% by weight polyolefin resin and from about 65% to about 25% by weight of filler.
- 15 4. The laminate of claim 1 wherein the surfactant treated nonwoven web comprises a spunbond polyolefin.
5. The laminate of claim 1 wherein the surfactant treated nonwoven web comprises a spunbond of any of polypropylene, polyethylene, a copolymer of polypropylene, and a copolymer of polyethylene.
- 20 6. The laminate of claim 1 wherein the surfactant treated nonwoven web comprises at least one layer of a meltblown polyolefin and at least one layer of a spunbond polyolefin.
7. The laminate of claim 1 wherein the filler of the stretchable film laminate comprises CaCO_3 .
8. The laminate of claim 1 wherein the laminate, tested per NFPA 702-1980, meets the 20 second or greater flame propagation criteria for a Class 1 material.
- 25 9. The laminate of claim 1 comprising a surgical drape.
10. The laminate of claim 1 wherein the laminate has a moisture vapor transmission rate of at least about 300 g/m²/24 hours.

24. The breathable laminate of claim 16 wherein the laminate has a moisture vapor transmission rate of at least about 300 g/m²/24 hours.

25. The breathable laminate of claim 16 wherein at least one layer of the multilayer film comprises a percentage of ethylene vinyl acetate.

5 26. The breathable laminate of claim 16 wherein at least one layer of the multilayer film comprises a metallocene linear low density polyethylene.

27. The breathable laminate of claim 16 wherein at least one layer of the multilayer film comprises a linear low density polyethylene.

10 28. The breathable laminate of claim 16 wherein at least some of the bond points form cohesive attachments between the web and the multilayer film.

10020298.121201